



** Please note that the material composition in different grades as shown below might have slight variation in actual chemistry and hence table below is for reference purposes only.*

Copper-H65		Cu		Zn		Pb		Fe	
		min	max	min	max	min	max	min	max
GB	H65	64%	68.5%	31%	36%	-	0.15%	-	0.05%
DIN	CuZn33	66%	68%			-	0.05%	-	0.05%
UNS	C26800	64%	68.5%			-	0.09%	-	0.05%
EN	CW506L	66%	68%			-	0.05%	-	0.05%
BS	CZ107	64%	67%	32.4%	36%	-	0.1%	-	0.1%
STAR Standard	H65	64%	68.5%	31%	36%	-	0.15%	-	0.05%