

**Data sheet: laser melting powder titanium alloy Ti6Al4V (grade 23)<sup>[a]</sup>  
Processed using AM250 with 200 W laser**

Powder composition / percent by mass								
Ti	Al	V	Fe	O	Residual	C	N	H
Balance	5.5 to 6.5	3.5 to 4.5	<0.25	<0.13	<0.1 each <0.4 total	<0.08	<0.03	<0.0125

**Material Properties**

High specific strength  
High corrosion resistance  
Excellent biocompatibility  
Good osseointegration  
Low thermal expansion  
Low thermal conductivity

**Applications**

Medical implants  
Surgical tools  
Aerospace and defence  
Motor sport  
Jewellery and art  
Maritime applications  
High-end sports equipment

Mechanical data	Stress relieved <sup>[b]</sup>		Test / ISO standard where applicable
	Min	Max	
Tensile strength (UTS) / MPa <sup>*</sup>	1 155	1 197	BS EN ISO 6892-1:2009
Yield strength (0.2%) / MPa <sup>*</sup>	1 070	1 111	BS EN ISO 6892-1:2009
Elongation at break / % <sup>*</sup>	2	8	BS EN ISO 6892-1:2009
Hardness / Vickers HV0.5 <sup>*</sup>	361	376	BS EN ISO 6507-1:1998
Surface roughness in X, Y / R <sub>a</sub> μm	4	6	JIS B 0601-2001 (ISO 97)
Surface roughness in Z / R <sub>a</sub> μm	4	7	JIS B 0601-2001 (ISO 97)
<b>Generic data</b>			
Density	4.42 g/cm <sup>3</sup>		Generic wrought material
Thermal conductivity at 20 °C	6 W/m·K to 8 W/m·K		Generic wrought material
Melting range	1 635 °C to 1 665°C		Generic wrought material
Coefficient of thermal expansion <sup>[c]</sup>	8 × 10 <sup>-6</sup> K <sup>-1</sup> to 9 × 10 <sup>-6</sup> K <sup>-1</sup>		Generic wrought material

\* Tested by Nadcap and UKAS accredited independent laboratory

Minimum and maximum values quoted are  $\bar{x} \pm \sigma$ , test samples were built in both horizontal and vertical directions.

[a] Also referred to as ELI, Extra Low Interstitial.

[b] 30 μm layers on AM250 and stress-relieved under argon at 730 °C for 2 hours, machined.

[c] Mean between 0 °C and 100 °C.

©2014 Renishaw plc. All rights reserved.

Renishaw has made considerable efforts to ensure the content of this document is correct at the date of publication but makes no warranties or representations regarding the content. Renishaw excludes liability, howsoever arising, for any inaccuracies in this document.

**RENISHAW** and the probe symbol used in the RENISHAW logo are registered trade marks of Renishaw plc in the United Kingdom and other countries.

**apply innovation** and names and designations of other Renishaw products and technologies are trade marks of Renishaw plc or its subsidiaries.

All other brand names and product names used in this document are trade names, trade marks, or registered trade marks of their respective owners.

**Renishaw plc**  
Whitebridge Way  
Whitebridge Park, Stone  
Staffordshire ST15 8LQ  
United Kingdom

**T** +44 (0) 1785 285000  
**F** +44 (0) 1785 885001  
**E** additive@renishaw.com

[www.renishaw.com/additive](http://www.renishaw.com/additive)



Values quoted are typical values for the AM process.

All information is based on results gained from experience and tests and is believed to be accurate but is given without acceptance of liability for loss or damage attributable to reliance thereon. Users should always carry out sufficient tests to establish the suitability of any products for their intended applications.

No guarantees of machine performance are expressed or implied by these data and Renishaw reserves the right to update them at any time.

©2014 Renishaw plc. All rights reserved.

Renishaw has made considerable efforts to ensure the content of this document is correct at the date of publication but makes no warranties or representations regarding the content. Renishaw excludes liability, howsoever arising, for any inaccuracies in this document.

**RENISHAW** and the probe symbol used in the RENISHAW logo are registered trade marks of Renishaw plc in the United Kingdom and other countries.

**apply innovation** and names and designations of other Renishaw products and technologies are trade marks of Renishaw plc or its subsidiaries.

All other brand names and product names used in this document are trade names, trade marks, or registered trade marks of their respective owners.